

# DPF 8200 High Tack

### Industrial Grade Film for Outdoor Wall and Low Surface Energy Substrates

DPF 8200 High Tack is a 3.5-mil (90 micron) satin white, high-tensile, PVC film with aggressive, permanent pressure-sensitive adhesive. The film is made of a 100% engineering-grade facestock with a polycoated lay-flat liner. The unique low shrink adhesive system enhances dimensional stability, improving printer handling and converting time. Designed to adhere to slightly textured outdoor wall substrates such as brick, tile, and concrete, the film also has exceptional performance on low surface energy substrates such as polypropelyne, polyethylene, and powder coated paints. DPF 8200 High Tack is rated for outdoor durability up to 7 years\* (unprinted). Using Arlon's recommended installation tips for walls, the film conforms well to flat surfaces with slight contours.

# **APPLICATIONS & FEATURES**

- Designed for outdoor wall and low surface energy substrates.
- Enhanced dimensional stability from beginning to end of application.
- Easy to convert, print, and apply, optimizing your workflow.
- Digital printing with a wide variety of direct print systems.

**PERFORMANCE & PHYSICAL DATA** 

### **COMPATIBLE OVERLAMINATES**

	OVERLAMINATE	APPLICATION USES*
		Outdoor Wall Graphics
8	SERIES 3210	Large Graphics
5	SERIES 3220	<ul> <li>Low Surface Energy Plastics</li> </ul>
5	SERIES 3420	• Decals
		• General Signage

\* Cast Laminate Recommended for Applications with Slight Contours & Textures

Certified for HP Latex Inks

#### **TYPICAL VALUE** PROPERTY TEST METHODS SURFACE FINISH Gloss Meter 60° Reflection 40 to 60 Gloss Units THICKNESS 3.5-mil (90 micron) Micrometer, Federal Bench Type Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. **TENSILE STRENGTH** 13.0 lb/in 2.3 kg/cm (5.1 mm/s), web direction ELONGATION Instron Tensile Tester as above > 150% SHELF LIFE (IN BOX) Ideal Storage Temperature 70°F (21°C) and 50% relative humidity 1 year from factory shipment APPLICATION 50°E to 80°E 10°C to 27°C On clean, dry substrate **TEMPERATURE RANGE** optimum optimum SERVICE -65°F to 225°F -54°C to 107°C On clean, dry substrate **TEMPERATURE RANGE** DIMENSIONAL STABILITY 158°F (70°C), 48 hours < 50 mil < 1.27 mm PEEL ADHESION PSTC-1, 15 min, 70°F (21°C) 4.0 lb/in 0.71 kg/cm LINER RELEASE TLMI Release at 90°, 300 in/min (760 cm/min) 50 g/2 in 9.8 g/cm

\* Outdoor durability for vertical masonry surfaces rated up to 6 months and up to 1 year for vertical exposure on flat surfaces. This is contingent upon no rain or harsh outdoor weather conditions.

Standard Terms & Conditions Apply

A: 🏮 200 Boysenberry Lane, Placentia, CA 92870, USA

: • North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

800 232 7161/+1 714 985 6300 +31 70 354 4311

800 329 2756 +31 70 355 7721

### arlon.com

## **TERMS & CONDITIONS**

The following is made in lieu of all warranties expressed or implied:

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

February 2018

USA: a 200 Boysenberry Lane, Placentia, CA 92870, USA EUROPE: <sup>a</sup> North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands 300 232 7161/+1 714 985 6300 +31 70 354 4311 800 329 2756 +31 70 355 7721

### arlon.com