

					4.
- R	eco	mn	nei	nda	100

Product Overview			
Product Code	EH9020		
Industry	Inks		
Application	Screen Printing		
Category	White Inks		
Chemistry	Plastisol		
Substrate(s)	Cotton		
Best Used By	12 months		
Certification(s)	ISO9001		
Curing:			
Fusion Temperature	320 °F		
Gel Point	150 °F		
Performance:			
Viscosity	Medium		
Coverage	High Opacity		
After Flash Tack	Low		
Squeegee:			
Squeegee Profile	Square		
Squeegee Type	Polyurethane		
Squeegee Speed	Medium/High		
Screen:			
Mesh	86 to 305		
Emulsion Type	Direct		
Cleanup	Non-hazardous screen wash		

Last Change: Feb 2017

# NPT SILKY COTTON WHITE

NPT SILKY Cotton White is designed for maximum smoothness and opacity on cotton fabrics. NPT SILKY Cotton White is opaque, with excellent matting characteristics. This smooth, creamy consistency is easy to print with on both manual and automatic presses. NPT SILKY Cotton White is fast flashing, allowing for shorter dwell times and faster production rates. NPT SILKY Cotton White works well as a highlight white or a stand-alone white.

## Instructions

For best results, flood the image and print using a sharp 70 durometer squeegee. A 70 durometer or 65/90/65 durometer squeegee may be used when a very heavy deposit is required. NPT SILKY Cotton White will print through screen meshes in the range of 86-305 MCI (32-120 MC cm). For fine deposit, use 160 MCI (62 MC cm) mesh or higher when necessary. Coarse meshes (86-110 MCI, 34-43 MC cm) are recommended for a thicker ink deposit which may be needed for heavy cotton fleece fabric. Additives: NPT SILKY Cotton White is a ready-to-print ink. Reduce, only if necessary, using curable reducer. Reducing the viscosity will also reduce the opacity and coverage of the ink. Please test before production run.

Flashing: Parameters vary between all flash units. Flash for 2-3 seconds with the ink deposit reaching 150-250°F (65-121°C). Ink should be dry and without tack. Warning: Over flashing can cure the ink and prevent adhesion between coats of ink.

Curing: Cure at  $320^{\circ}$ F ( $160^{\circ}$ C) over a 60-90 second period, depending on oven type and thickness of ink deposit. A thicker deposit will take longer to cure as the heat must penetrate through the entire ink layer.

#### Recommendation

Do not dry clean, bleach, or iron the printed image.

## Statement

Rutland Plastic Technologies does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSIA HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP), benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DOP), (DIBP) Di-isobutyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Claira High Opacity Non-Phthalate Inks. Rutland Plastic Technologies does not test the final product for amounts of the aforementioned phthalate plasticizers and esters and encourages all users to conduct testing for their intended use.

# **Disclaimer:**

Not all Rutland products are available in every country. Please check with your local representative for availability. The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.