

Recommendations

Product Overview

Product Code	EH0540
Industry	Inks
Application	Screen Printing
Category	Mixing Inks
Sub-Category	Base
Chemistry	Plastisol
Substrate(s)	Cotton
Best Used By	12 months
Certification(s)	ISO9001

Curing:

Fusion Temperature	320 °F
Gel Point	160 °F

Performance:

Viscosity	High
Coverage	High Opacity
After Flash Tack	Low

Squeegee:

Squeegee Profile	Square
Squeegee Type	Polyurethane
Squeegee Speed	Medium/High

Screen:

Mesh	86 to 280
Underlay	NPT Whites
Emulsion Type	Capillary film, Direct
Cleanup	Environmentally friendly screen wash

Additives:

Thickener	M00010 Thickener #10
-----------	----------------------

Storage:

Storage Temperature	65°F - 95°F (18°C - 35°C)
Storage Notes	Avoid direct sun.

Last Change: Nov 2016

NPT VO BASE

EH0540 NPT VO Base is now formulated as a press-ready non-phthalate plastisol base for mixing colors using C3 NPT Color Boosters and printing on 100% Cotton or over a NPT low bleed underlay when printing on poly/cotton blends. Short body and very low wet tack for easy printing with no build-up. Fast shearing action means higher press speeds. Easy to use, helps maintain printable viscosity when mixed with C3 Color Boosters. Maintains non-phthalate status if mixed with C3 Color boosters.

Features

-
-
-
-

Instructions

Mix EH0540 NPT VO Base with C3 Color Boosters and print directly onto substrates. EH0540 is normally printed through mesh ranges from 86-280 mc in. (34-110 mc. CM.) Recommend 70-80 Durometer squeegee with sharp edge for maximum definition. Proper cure is achieved when garment reaches 320°F (160° C.).

Recommendation

Claira Colors™, bases, modifiers and additives should be mixed in clean vessels using clean mixer blades and utensils. Any contamination from other ink sources or non approved additives could make Claira Colors™ test positive for the restricted phthalates. Do not dry clean, bleach, or iron the printed image.

Statement

Rutland Plastic Technologies does not knowingly add plasticizers containing the phthalates listed and outlined in California Bill 1108, CPSIA HR-4040 and Oeko-tex Standard 100. The plasticizers identified may include di-(2-ethylhexyl) phthalate (DEHP), dibutyl phthalate (DBP), benzyl butyl phthalate (BBP), diisononyl phthalate (DINP), diisodecyl phthalate (DIDP), di-n-octyl phthalate (DnOP), (DIBP) Di-isobutyl, and (DMP) Dimethylphthalate, including esters of ortho-phthalic acid and are not direct ingredients in the manufacture of Claira High Opacity Non-Phthalate Inks. Rutland Plastic Technologies does not test the final product for amounts of the aforementioned phthalate plasticizers and esters and encourages all users to conduct testing for their intended use.

Disclaimer:

Not all Rutland products are available in every country. Please check with your local representative for availability. The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.