AQUARIUS WATERBASED



ZODIAC* ECOCENTRIC INKS

PRODUCT INFORMATION BULLETIN

Aquarius™ Soft Base Range

RECOMMENDED PARAMETERS



Fabric Types

100% Cotton, blends or synthetic fabrics.



Mesh

Count: 110-320T/in (43-125T/cm) Tension: 18-35n/cm3



Squeegee

60-90-60

Profile: sharp, square

Stroke: x2 stroke, medium speed

Angle: 10-15%



Stencil

Water Resistant Emulsion Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: Not recommended Cure: 90 seconds at 330°F (165°C)



Pigment Loading

Maximum 6%



Aquarius™ Additives

Aquarius™ Softener 1-5% Aquarius™ Thickener 0.1-1% Aquarius™ Retarder Gel 1-5%



Storage

Store in sealed containers 12 months from manufacture >40°F (5°C) <77°F(25°C)




Clean Up

Water & mild detergent



Health & Safety

SDS: www.avient.com/resources/ safety-data-sheets or contact your local CSR



HIGHLIGHTS

Supersoft hand feel

Suitable for vector or tonal artwork

Prints wet on wet

Excellent wash durability and crock

Bright colors

PRINTING TIPS

✓ Use 110-320T (43-125T) mesh for best performance and color brightness.

Print with 1/16" or 2mm off contact

Print one stroke

Print wet on wet. Light to dark

Clean the stencil area when stopped to prevent screen blockages

Prints should be cured at 330°F /165°C for 90 seconds. Check the cure temp at the ink surface

Colors should be made in accordance with Aquarius™ IMS Pantone® mixing system with a maximum of 6% pigment loading to ensure crock performance is maintained

Test all prints for color fastness and print durability before starting the production run

COMPLIANCE

Water based, non PVC, non phthalate

Wisit www.avient.com/products/screen-printing-inks/zodiac-aquarius for more information

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT SPECIALTY

V1,02 (Modified: 06/11/2020)

2020, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales represententive for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES, OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.