



MPC122

HBPT High Build Etching Primer

74 770SP

Matthews 74 770SP HBPT is a quality, two-component, high build self-etching metal primer. It is designed for use on raw aluminum and steel.

74 770SP HBPT etches the properly prepared metal surface to provide outstanding paint adhesion and corrosion resistance.

This fast drying etching primer is buff colored and will fill a 120g DA sand scratch with a two-coat application.



Features:

Benefits:

Topcoat with any Matthews Acrylic Polyurethane finishes	Versatile, multi-purpose
Easy mix ratio	Less time mixing
Anti-corrosion properties	Provides excellent corrosion protection
Etching properties	Great adhesion to properly prepared aluminum or steel
14 day pot life	Mix once and use for two weeks

Compatible Surfaces:

74 770SP High Build Etching Primer may be applied over properly prepared:

- Aluminum
- Steel

Associated Products:

74 766SP Activator

74 770SP

Directions for Use

Estimated Drying Times:



Air-Dry @ 50% Relative Humidity, 70°F/21°C
Dust Free 15 - 25 minutes
Dry to Touch 30 minutes*
Dry to Topcoat 30 minutes - 24 hours (max)**

*If necessary to remove dust nibs, 74 770SP High Build Etching Primer may be sanded with 220 - 320g after 2 - 4 hours (do not wet sand etch primers).

**After 24 hours, sand with a 220-400 grit dry, or equivalent sanding pad. Do not sand below minimum dry film thickness, otherwise reprime before topcoating.

Note: Etch primers should never be wet sanded or exposed to moisture or weather before topcoating.

Equipment Cleaning:

Clean equipment promptly with lacquer thinner or equivalent cleaning solvent.

Note: Do not leave mixed material in equipment.

Technical Data:

VOC Information

VOC Actual RTS	6.08 lbs/gal
VOC Actual RTS	728 g/L
VOC Regulatory (less water less exempt) RTS	6.15 lbs/gal
VOC Regulatory (less water less exempt) RTS	736 g/L

For complete VOC information, visit MatthewsPaint.com > Quick Links > VOC Data

Performance Characteristics

Volume solids (RTS)	10.08%
Theoretical Coverage (1 mil @ 100% transfer efficiency)	161 sq.ft./RTS gal
Application Conditions - Temperature	60°F (16°C) Minimum 100°F (38°C) Maximum
Application Conditions - Relative Humidity	85% maximum 5° above dew point

Important: The contents of this package may have to be blended with other components before the product can be used. Before opening the packages, be sure you understand the warning messages on the labels of all components, since the mixture will have the hazards of all its parts. Improper spray technique may result in a hazardous condition. Follow spray equipment manufacturer's instructions to prevent personal injury or fire. Follow directions for respirator use. Wear eye and skin protection. Observe all applicable precautions.

See Safety Data Sheet and Labels for additional safety information and handling instructions.

EMERGENCY MEDICAL OR SPILL CONTROL INFORMATION - US (412) 434-4515; CANADA (514) 645-1320; Mexico 01-800-00-21-400
Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public. Products mentioned may be hazardous and should only be used according to directions, while observing precautions and warning statements listed on label. Statements and methods described are based upon the best information and practices known to Matthews Paint. Procedures for applications mentioned are suggestions only and are not to be construed as representations or warranties as to performance, results, or fitness for any intended use, nor does Matthews Paint warrant freedom from patent infringement in the use of any formula or process set forth herein. If you require technical assistance, please call us toll-free 800/323-6593.

74 770SP

HBPT High Build Etching Primer



The World's Finest Coating For Architectural Signage

760 Pittsburgh Drive
Delaware, OH 43015
Toll Free: 800/323-6593
Toll Free FAX: 800/947-0377